

Post-It® Fax Note	7671	Date	9/14/06	# of pages	3
To	CHIP TOKAR				
From	Samara Sears				
Co./Dept.	Co.				
Phone #	Phone # 517 322 1357				
Fax #	419 882 8772				

FILE 300

Control Section Identification	
Job No.	
Laboratory No.	06A-10205*
Date	September 14, 2006

Report on Sample of **HOT MIX ASPHALT AGGREGATE**

Date Sampled	Not Stated	Date Received	
Source of Material	TIRB ASI# 81-021	Quantity Represented	
Sampled From			
Submitted By	CHIP TOKAR - THE STANLEY GROUP		
Intended Use	Bituminous Mixtures	Specification	34R 2003 Std Spcc Supp

**TEST RESULTS**


COMPOSITION OF SAMPLE

ROCK TYPE	PERCENT	WEAR TRACK AWI	CALCULATED AWI
IGNEOUS/METAMORPHIC	30.7	370	113.6
SEDIMENTARY			
Carbonates	57.3	250	143.2
Sandstone	0.4	490	2.0
Siltstone		475	
Shale	2.1	335	7.0
Clay Ironstone		275	
Chert	9.5	345	32.8
Crag		435	

Weighted Sample AWI .....	298.6
Uncrushed Particles, % .....	100
AWI Reduction Based on Uncrushed	
Reduction in Percent .....	26.0
Adjusted AWI .....	221.0

REMARKS: \*FOR INFO ONLY

cc: A. Robords  
 R. Muethel  
 F. TOKAR - THE STANLEY GROUP

  
 Geologist