

Post-it [®] Fax Note	7671	Date	# of pages 3
To CHIP TOKAR	From Jamaca Sears	Co./Dept.	Co.
Phone #	Phone # 517 382-1357	Fax #	Fax #
Fax # 419 882 8772			

Control Section Identification	
Job No.	
Laboratory No.	06A-10206*
Date	September 14, 2006

FILE 300

Report on Sample of **HOT MIX ASPHALT AGGREGATE**

Date Sampled	Not Stated	Date Received	
Source of Material	SMR- PLANT 305 ASI# 30-073	Quantity Represented	
Submitted By	CHIP TOKAR - THE STANSLEY GROUP	Intended Use	Bituminous Mixtures
Specification	34R		2003 Std Spec Supp

TEST RESULTS

COMPOSITION OF SAMPLE

ROCK TYPE	PERCENT	WEAR TRACK AWI	CALCULATED AWI
IGNEOUS/METAMORPHIC	27.7	370	102.5
SEDIMENTARY			
Carbonates	58.1	250	145.2
Sandstone	2.3	490	11.3
Siltstone		475	
Shale	1.7	335	5.7
Clay Ironstone		275	
Chert	10.2	345	35.2
Crag		435	

Weighted Sample AWI	299.9
Uncrushed Particles, %	100
AWI Reduction Based on Uncrushed Reduction in Percent	26.0
Adjusted AWI	221.9

REMARKS: * FOR INFO ONLY

cc: A. Robords
R. Muethel
F. TOKAR - THE STANSLEY GROUP


Geologist