

Post-it\* Fax Note 7671 Date 9/14/06 # of pages 3  
 To CHIP TOKAR From Samuel Sears  
 Co./Dept. Co.  
 Phone # Phone # 517 322-1357  
 Fax # 419 882 8772 Fax #

FILE 300  
 Control Section Identification  
 Job No.  
 Laboratory No. 06A-10204\*  
 Date September 14, 2006

Report on Sample of HOT MIX ASPHALT AGGREGATE  
 Date Sampled Not Stated Date Received \_\_\_\_\_  
 Source of Material SMR PLANT 311 ASI# 46-051  
 Sampled From \_\_\_\_\_ Quantity Represented \_\_\_\_\_  
 Submitted By CHIP TOKAR - THE STANLEY GROUP  
 Intended Use Bituminous Mixtures Specification 34R 2003 Std Spec Supp

**TEST RESULTS**


COMPOSITION OF SAMPLE

ROCK TYPE	PERCENT	WEAR TRACK AWI	CALCULATED AWI
IGNEOUS/METAMORPHIC	27.1	370	100.3
SEDIMENTARY			
Carbonates	65.3	250	163.2
Sandstone	0.3	490	1.5
Siltstone		475	
Shale	5.8	335	19.4
Clay Ironstone		275	
Chert	1.5	345	5.2
Crag		435	

Weighted Sample AWI ..... 289.6  
 Uncrushed Particles, % ..... 100  
 AWI Reduction Based on Uncrushed  
 Reduction in Percent ..... 26.0  
 Adjusted AWI ..... 214.3

REMARKS: \* FOR INFO ONLY

cc: A. Robords  
 R. Muethel  
 F. TOKAR - THE STANLEY GROUP

  
 Geologist